

Revision: 04

Approved: 20.12.2023

## **Technical data sheet**

## EGGER PerfectSense® Premium Laminates Gloss



### Description

EGGER PerfectSense Premium Laminates Gloss are decorative, UV lacquer coated laminates. They have a multi-layer structure and consist of several impregnated core layers, an impregnated decor paper and a gloss lacquer surface.

Description: EGGER PerfectSense Premium Laminates Gloss

Type of material: **HGS** (<u>H</u>orizontal <u>G</u>eneral-purpose <u>S</u>tandard) in accordance to EN 438-3 vertical surfaces or horizontal surfaces with light stress, e.g. furniture top panels

### **Availability**

EGGER PerfectSense Premium Laminates Gloss are part of the **EGGER Decorative Collection** in the nominal thickness of 0.80 mm. They are available in selected decors from stock and in quantities of one, according to the country-specific delivery lists. Further decors are produced with a minimum order quantity of 260 m² per version and always made to order – see section "Delivery form".

#### **Technical data**

Laminates with a lacquer-based surface are currently not described by or classified in the EN 438 standard. In accordance to the EN 438-3 EGGER PerfectSense Premium Laminates Gloss can be assigned to the standard classification  $\underline{\mathsf{HGS}}$  ( $\underline{\mathsf{H}}$ orizontal  $\underline{\mathsf{G}}$ eneral-Purpose  $\underline{\mathsf{S}}$ tandard).

Property	Test standard	Unit or feature	Value
Resistance to surface wear*	EN 438-2	Revolutions	
		Initial point	≥ 150
Resistance to impact by small diameter ball*	EN 438-2	N	
		nominal thickness 0.80 mm	≥ 20
Resistance to scratching*	EN 438-2	Rating	≥ 4 <sup>1)</sup>
Thickness	EN 438-2	mm	± 0.10
Length and width <sup>2)</sup>	EN 438-2	mm	+ 10 / - 0
Flatness <sup>3)</sup>	EN 438-2	mm/m (max.)	60







Revision: 04

Approved: 20.12.2023

Property	Test standard	Unit or feature	Value
Resistance to water vapour	EN 438-2	Rating (min.)	
		gloss surface	3
Resistance to dry heat (160 °C)	EN 438-2	Rating (min.)	
		gloss surface	3
Dimensional stability at elevated temperatures	EN 438-2	% max.	
		L <sup>a</sup>	0.55
		T⁵	1.05
Resistance to wet heat (100 °C)	EN 438-2	Rating (min.)	
		gloss surface	3
Resistance to staining	EN 438-2	Rating (min.)	
		Groups 1 and 2	5
		Group 3	4
Lightfastness (Xenon arc lamp)	EN 438-2	Grey scale rating	4 to 5

<sup>\*</sup> Property is relevant for the classification of the material type.

## Form of delivery

Our order-related delivery options in overview:

Options EGGER PerfectSense Premium Laminates Gloss		
Texture	PG	
Nominal thickness	0.80 mm	
Maximum length	4,100 mm; 50 mm grid	
Minimum length	800 mm; 50 mm grid	
Standard length	2,464; 2,800; 3,050 and 4,100 mm	
Maximum width	1,310 mm	
Individual width	on request	
Standard width	950; 1,020; 1,245 and 1,310 mm	
Minimum quantity	260 m²	
Protection film	with protective film as standard	

# **Technical application note**

The high gloss PerfectSense Premium Gloss surface is based on a UV lacquer finish with anti-fingerprint properties. The lacquer surface has "no texturing", so signs of wear may appear when subjected to mechanical stress. With medium to dark solid and printed decors, traces of use are more noticeable than with light decors. This is not a functional impairment of the surface, but an impairment based on visual aspects.

Slight colour deviations in the same product are possible due to tolerances in the primary materials used. Components that are used next to each other should therefore be checked for colour uniformity. A deviation in colour and surface between the





 $<sup>^{1)} \</sup>ge 90$  % continuous double circle of scratch marks clearly visible.

<sup>&</sup>lt;sup>2)</sup> Tolerances for cut-to-size panels shall be agreed between EGGER and purchaser.

<sup>&</sup>lt;sup>3)</sup> Provided that the laminate is stored in the manner and conditions recommended by EGGER.

 $L^a = in$  the longitudinal direction of the fibrous sheet material (normally the direction of the longest dimension of the laminate).

T<sup>b</sup> = in the cross-longitudinal direction of the fibrous sheet material (at right angles to direction L).



Revision:

04

Approved: 20.12.2023

EGGER reference colour sample and the customer's test piece is permissible in accordance with EN 438. Due to the production that differs by product, colour and surface differences can also occur between different products (e.g. faced board, laminate, edging) with the same decor-texture combination. For an accurate representation of the colour, order a sample in the relevant product.

PerfectSense Premium Laminates Gloss are fitted with a protective film to protect the surface during transport and processing. The self-adhesive protective film is provided for a limited period of time, i.e. it must be removed immediately after processing the laminate, but no later than 6 months after the delivery date. The temperature resistance of the protective film is approx. 140°C.

Please find more detailed information in the technical leaflet "EGGER Laminates with protective film".

### Care and cleaning recommendation

EGGER PerfectSense Premium Laminates Gloss do not require any special care due to their resistant and hygienic, dense surfaces. The surfaces are generally easy to clean. Do not use sanitary cleaners or detergents with abrasive components, as using such cleaners may lead to changes in the degree of gloss and/or scratch the material.

For detailed information, please refer to the leaflet "Cleaning and care recommendations for EGGER product surfaces".

#### Additional documents / Product information

You will find further information in the following documents:

- Processing instructions "EGGER Laminates"
- Technical leaflet "EGGER Laminates balancer"
- Technical leaflet "EGGER Laminates with protective film"
- Technical leaflet "FGGFR Laminates for whiteboard use"
- Technical leaflet "Resistance to chemicals EGGER Laminates"
- Technical leaflet "Cleaning and care recommendations for EGGER product surfaces"

#### Provisional note:

This technical data sheet has been carefully drawn up to the best of our knowledge. The information provided is based on practical experience, in-house testing and reflects our current level of knowledge. It is intended for information only and does not constitute a quarantee in terms of product properties or its suitability for specific applications. We accept no liability for any mistakes, errors in standards, or printing errors. In addition, technical modifications may result from the continuous development of EGGER PerfectSense Premium Laminates Gloss, as well as from changes to standards and public law documents. The contents of this technical data sheet should therefore not be considered as instructions for use or as legally binding. Our General Terms and Conditions apply



